


# Sound Absorption Graph

The following values reflect the acoustic properties of the product as tested in accordance with ASTM C423-09a.



200	250	315	400	500	630	800	1000	1250	1600	2000	2500	NRC	SAA
0.12	0.16	0.32	0.43	0.64	0.77	0.97	1.02	1.04	1.06	1.06	1.04	0.70	0.72