


Sound Absorption Graph

The following values reflect the acoustic properties of the product as tested in accordance with ASTM C423-09a.



200	250	315	400	500	630	800	1000	1250	1600	2000	2500	NRC	SAA
0.41	0.47	0.68	0.73	0.88	0.95	1.08	1.23	1.39	1.49	1.52	1.57	1.05	1.03