


# Sound Absorption Graph

The following values reflect the acoustic properties of the product as tested in accordance with ASTM C423-09a using Type A mounting.



	NRC	SAA	200	250	315	400	500	630	800	1000	1250	1600	2000	2500
<b>A 18 mm</b>	0.60	0.58	0.10	0.12	0.18	0.30	0.44	0.63	0.72	0.81	0.87	0.91	0.94	0.97