


Sound Absorption Graph

The following values reflect the acoustic properties of the product as tested in accordance with ASTM C423-09a.



200	250	315	400	500	630	800	1000	1250	1600	2000	2500	NRC	SAA
0.25	0.23	0.34	0.46	0.60	0.73	0.76	0.87	0.96	0.97	0.94	0.91	0.65	0.67