


Sound Absorption Graph

The following values reflect the acoustic properties of the product as tested in accordance with ASTM C423-09a.



200	250	315	400	500	630	800	1000	1250	1600	2000	2500	NRC	SAA
0.03	0.02	0.07	0.09	0.13	0.24	0.34	0.46	0.58	0.70	0.77	0.86	0.35	0.36