


Sound Absorption Graph

The following values reflect the acoustic properties of the product as tested in accordance with ASTM C423-09a.



200	250	315	400	500	630	800	1000	1250	1600	2000	2500	NRC	SAA
0.17	0.23	0.34	0.50	0.63	0.77	0.86	0.92	1.03	1.00	0.99	0.98	0.70	0.70