




Sound Absorption Graph

The following values reflect the acoustic properties of the product as tested in accordance with ASTM C423-09a.



200	250	315	400	500	630	800	1000	1250	1600	2000	2500	NRC	SAA
0.35	0.45	0.68	0.79	0.99	1.13	1.20	1.22	1.26	1.23	1.22	1.17	0.95	0.97