


Sound Absorption Graph

The following values reflect the acoustic properties of the product as tested in accordance with ASTM C423-09a.



	200	250	315	400	500	630	800	1000	1250	1600	2000	2500	NRC	SAA
Madera A	0.07	0.09	0.18	0.24	0.36	0.53	0.69	0.80	0.92	1.00	1.02	1.06	0.55	0.58
Madera B	0.06	0.07	0.18	0.25	0.39	0.54	0.72	0.83	0.93	0.99	1.02	1.07	0.60	0.59
Madera C	0.07	0.11	0.22	0.27	0.42	0.60	0.76	0.87	0.96	1.03	1.03	1.08	0.60	0.62