




Sound Absorption Graph

The following values reflect the acoustic properties of the product as tested in accordance with ASTM C423-09a.



200	250	315	400	500	630	800	1000	1250	1600	2000	2500	NRC	SAA
0.25	0.34	0.62	0.82	1.05	1.14	1.23	1.25	1.23	1.22	1.20	1.18	0.95	0.96