


Sound Absorption Graph

The following values reflect the acoustic properties of the product as tested in accordance with ASTM C423-09a.



200	250	315	400	500	630	800	1000	1250	1600	2000	2500	NRC	SAA
0.97	1.00	0.96	0.85	0.71	0.82	0.90	0.91	0.96	1.00	0.99	0.99	0.90	0.92