

NWAA Labs

90 Tower Blvd, Elma, WA 98541, Phone: (253) 973-1018
Email address: audio_ron@msn.com

SOUND ABSORPTION TEST REPORT #: NWAB181101-01

Client: Akustus Industries, Inc.
518 East Kent Avenue South
Vancouver, BC, Canada, V5X 4V6

Test Date: 01 November, 2018
Report Date: 3 March, 2019
Test Specimen: polyester fiber panels, 2ft by 4 ft

INTRODUCTION

The methods and procedures used in this test conform to the provisions and requirements of ASTM Procedure C 423-09a, *Standard Test Method for Sound Absorption Coefficients by the Reverberation Room Method*. Copies of the test standards are available at www.astm.org. The test chamber is a cuboid, 12.79 m (42.0 ft) long by 10.75 m (35.3 ft) wide by 5.31 m (17.4 ft) high, and volume is 737.4 m³ (26041.0 ft³). There are six fixed surfaces in the reverberation chamber. There are three sources consisting of two dodecahedron loudspeakers mounted in the two upper corners and one sub-woofer located below one of the dodecahedrons. We utilize six Earthworks M-30 Omni directional microphones to gather the data. This test report relates only to the item(s) tested. Any advertisement that utilizes this test report or test data must not imply product certification or endorsement by NWAA Labs and has to include all pages of the report.

DESCRIPTION OF TEST SPECIMEN

The test specimen consisted of fifteen hanging panel units that were 121.92 cm (48.0 inch) long by 60.96 cm (24.0 inch) wide by 33.34 mm (1.31 inches) thick. These polyester fiber panels were then mounted in a Type J mounting, hanging from cables in six rows of alternating two and three panels on each cable. The cable where hung in rows that were not parallel to any wall surface. They were spaced is 0.75m (30 inches) and the spacing between panels on the same cable was 0.3m (12.0 inches). The lower edges of the samples were spaced to be 1m (39.9 inches) from the floor. This created a test sample with the overall dimensions of 3.05 m (10.0 ft.) by 3.66 m (12.0 ft.), and an overall weight of 68.18 kg (150.0 lbs.). (See pictures).

Test results are on the following pages.

Submitted by,
NWAA Labs Inc



Ron Sauro
NWAA Labs Inc



This page, by itself, does not constitute a full test report. Page 2 of 6



This page, by itself, does not constitute a full test report. Page 3 of 6

NWAA Labs, Inc.

90 Tower Blvd,
Elma, WA 98541
(253)-973-1018

Test #	NWAB181101-01
Test Date:	1-Nov-18
Mounting per ASTM E795-00:	J Mount
Area Tested: M ²	11.15
Temperature: °C	22
Barometer: pa	101500
Humidity: %	65

NRC	1.15
SAA	1.12

AKUSTUS polyester fiber baffles 2ft x 4ft

Frequency (Hz)	Absorption Coefficient	Absorption (m ²)	Absorption (sabins)
40Hz	0.06	0.65	7.00
50Hz	0.09	1.03	11.10
63Hz	0.14	1.59	17.10
80Hz	0.22	2.47	26.60
100Hz	0.21	2.36	25.40
125Hz	0.16	1.82	19.60
160Hz	0.37	4.09	44.00
200Hz	0.29	3.22	34.60
250Hz	0.41	4.53	48.80
315Hz	0.57	6.37	68.60
400Hz	0.80	8.94	96.20
500Hz	1.01	11.27	121.30
630Hz	1.21	13.53	145.60
800Hz	1.21	13.55	145.80
1000Hz	1.43	15.98	172.00
1250Hz	1.62	18.10	194.80
1600Hz	1.66	18.48	198.90
2000Hz	1.65	18.35	197.50
2500Hz	1.63	18.22	196.10
3150Hz	1.63	18.17	195.50
4000Hz	1.59	17.73	190.80
5000Hz	1.57	17.46	187.90
6300Hz	1.49	16.64	179.10
8000Hz	1.58	17.65	190.00
10000Hz	1.64	18.29	196.90

NWAA Labs, Inc.

90 Tower Blvd,
Elma, WA 98541
(253)-973-1018

Test #	NWAB181101-01
Test Date:	1-Nov-18
Mounting per ASTM E795-00:	A Mount
Number of Units	15
Temperature: °C	22
Barometer: pa	101500
Humidity: %	65

NRC	
SAA	

AKUSTUS polyester fiber baffles 2ft x 4ft				
Frequency (Hz)		Absorption (m ²)	Absorption (sabins)	
50Hz		0.65	7.00	
63Hz		1.03	11.10	
80Hz		1.59	17.10	
100Hz		2.47	26.60	
125Hz		2.36	25.40	
160Hz		1.82	19.60	
200Hz		4.09	44.00	
250Hz		3.22	34.60	
315Hz		4.53	48.80	
400Hz		6.37	68.60	
500Hz		8.94	96.20	
630Hz		11.27	121.30	
800Hz		13.53	145.60	
1000Hz		13.55	145.80	
1250Hz		15.98	172.00	
1600Hz		18.10	194.80	
2000Hz		18.48	198.90	
2500Hz		18.35	197.50	
3150Hz		18.22	196.10	
4000Hz		18.17	195.50	
5000Hz		17.73	190.80	
6300Hz		17.46	187.90	
8000Hz		16.64	179.10	
10000Hz		17.65	190.00	

NWAA Labs, Inc.

90 Tower Blvd,
Elma, WA 98541
(253)-973-1018

Test #	NWAB181101-01
Test Date:	1-Nov-18
Mounting per ASTM E795-00:	J Mount
Area Tested: M ²	11.15
Temperature: °C	22
Barometer: pa	101500
Humidity: %	65

NRC	1.15
SAA	1.12

AKUSTUS polyester fiber baffles 2ft x 4ft

